SEM® PLASTIC REPAIR STANDARD OPERATING PROCEDURE



Clean front and back with **Scuff & Clean** and damp, gray scuff pad. Rinse with water and dry or wipe with a clean, damp cloth until removed. Clean front and back with **SEM Solve, Plastic & Leather Prep** or **XXX Universal Surface Cleaner**. Wipe clean in one direction with dry, lint-free cloth.

PRODUCT LIST



2 SAND & DISH

REINFORCE & FILL BACK

On front side, sand repair area with P80 grit. Dish out damage with P36 grit disc at a low RPM. On back side, grind repair area with P36 grit disc at a low RPM. Blow off surfaces.

- i Paint does not need to be stripped from the repair if it has good adhesion.
- 1 Do not grind too fast and cause plastic to melt.
- (i) (Optional) Apply **XXX Adhesion Promoter** to all prepped surfaces.

Mask front side of repair to prevent repair material from flowing through. Apply **Plastic Repair Contouring Tape** (mesh only) to back side. Apply **Dual-Mix™ Multi-Plastic Repair Material** or **Dual-Mix Problem Plastic Repair Material** and cover mesh tape. Spread material firmly. Allow to set.

PRFP

Part	Product	Size		
38391	Scuff & Clean	Gallon Pump		
38398	Scuff & Clean	16 oz. Tube		
38371	SEM Solve	Gallon		
38373	SEM Solve	20 oz. Aerosol		
38374	SEM Solve	Square Quart		
38351	Plastic & Leather Prep	Gallon		
38353	Plastic & Leather Prep	16 oz. Aerosol		
38354	Plastic & Leather Prep	Cone Quart		
77721	XXX Adhesion Promotor	Gallon		
77723	XXX Adhesion Promotor	16 oz. Aerosol		
77724	XXX Adhesion Promotor	Cone Top Quart		
77771	XXX Universal Surface Cleaner	Gallon		
77774	XXX Universal Surface Cleaner	Quart		



4 REINFORCE & FILL FRONT

Remove tape from front. Fill front with **Dual-Mix Multi-Plastic Repair Material** or **Dual-Mix Problem Plastic Repair Material**. Spread material firmly and build up higher than panel to allow for sanding. Allow to set before sanding.

REINFORCE & FILL

Part	Product	Size
70007	Plastic Repair Contouring Tape	15' Roll
39767	Dual-Mix Problem Plastic Repair Material	7 oz. Cartridge
39847	Dual-Mix Multi-Plastic Repair Material	7 oz. Cartridge





WATCH & LEARN

Sand with P80 grit. Finish with P180 grit. If needed, use a skim coat of **Bumper Bite™ Flexible Glaze**, then sand with P180 − P320 grit.

 Refer to Plastic Refinishing SOP for refinishing steps.

WATCH THE VIDEO AT:

semproducts.com/sop-plastic-repair





SAND AND SKIM

Part	Product	Size	
4048	32 Bumper Bite FI	lexible Glaze 16 oz. Tube	

SEM Products, Inc. Rock Hill, SC 29730

Tech Support: 1-800-831-1122 Customer Care: 1-866-327-7829 semproducts.com



