

WORLD CLASS[™] 4.2 VOC EURO CLEAR TECHNICAL DATA SHEET

(i) Check local VOC regulations to ensure compliance of all products in your area.

DESCRIPTION

World Class 4.2 VOC Euro Clear is a high quality, national rule, two-component, urethane clearcoat for productive collision shops.

FEATURES

- 24 month warranty
- 2:1 Mix
- Excellent flow and leveling
- Exceptional gloss and DOI
- Chemical resistant
- · Easy to buff
- Excellent UV protection
- 4 activator speeds

SUITABLE SUBSTRATES

- · All automotive basecoat paint systems
- Fully cured refinish materials
- Properly prepped OEM finishes

TYPICAL PROPERTIES

Part:	Product Name:	Color:	Container:
50809	World Class 4.2 VOC Euro Clear	Clear	5 Liter
RTS weight	t solids:	39.1%	
RTS volume	e solids:	31.8%	
RTS VOC:		Max 4.2 lb/gal (504	l g/L)
Pot life:		1 Hour @ 70°F (21°C) and 50% RH	
Fluid tip size:		1.2mm – 1.4mm	
Inlet air pre	essure:	25 – 35 psi	
Coverage:		255 sq.ft./gal @ 2+	- mils DFT
Mil build per coat:		1.3 – 1.6	
Dust Time:		10 - 30 minutes	
Air dry time to buff:		4-8 hours	

HANDLING AND APPLICATION



PREPARATION:

After sanding primer, scuff any blend areas with **Scuff & Clean** according to directions. Clean surface with **SEM Solve** or **XXX Universal Surface Cleaner**. Apply basecoat per instructions and allow to fully flash dry.



MIXING:

Shake or stir thoroughly. Mix by volume:

2 Parts	1 Part
4.2 VOC Euro Clear	4.2 VOC Euro Activator

ACTIVATORS:

Part:	Product Name:	For:
50842	4.2 VOC Euro Extra Fast Activator	Spot and single panel repairs. 1-2 panels below 65°F (18°C)
50852	4.2 VOC Euro Fast Activator	Small parts, 1-2 panels. Larger jobs from 55°F (13°C)
50862	4.2 VOC Euro Medium Activator	2-3 panels. Larger jobs from 65°F (18°C)
50872	4.2 VOC Euro Slow Activator	3-5 panels. Larger jobs from 75°F (23°C)

ADDITIVES:

Part:	Product Name:	For:
50918	Accelerator	Reducing cure to handle times by up to 25%
50928	Extender	Extending pot life in hot and/or humid conditions

Note: The use of **Accelerator** may reduce time to buff by up to 30 minutes. For best performance when using **Accelerator**, complete buffing operation within 16-24 hours.

Thinning with reducer is not recommended. If used, amount should not exceed 5% by volume.



APPLICATION:

- **1.** Set air pressure to 8-10 psi at the cap for HVLP equipment.
- **2.** Use a spray gun equipped with a 1.2- 1.4 fluid nozzle.
- **3.** Spray two full wet coats, allowing 5-10 minutes between coats.



Allow 10 minute flash after last coat prior to force drying.

DRY TIMES:

Note: Dry and cure times are dependent on several factors including temperature, air-flow, film build, activator selection and humidity.

		Air Dry	Force Dry 30 min @140°F (60°C)
	To handle:	3-8 hours	After cool down
	To buff:	4-8 hours	After cool down
	To deliver:	8-24 hours	After cool down

Note: If recoating with clear only, sand with 1000 grit. If re-applying basecoat and clearcoat, sand with 600 grit.

Note: In cooler conditions, sanding and buffing will improve by extending cool down period by 60-90 minutes.



CLEANUP:

Use XXX Gun Cleaner or appropriate cleaning materials compliant with VOC regulations in your area.



STORAGE:

World Class 4.2 VOC Euro Clear should be stored in a cool dry place with adequate ventilation away from heat, sparks and flames. The shelf life for **World Class 4.2 VOC Euro Clear** is 5 years when stored under normal conditions. The shelf life for **World Class 4.2 VOC Euro Activators** is 3 years.

Part:	Product Name:	Size:
38371	SEM Solve	Gallon
38373	SEM Solve	20 oz. Aerosol
38374	SEM Solve	Quart
38375	SEM Solve	5 Gallon
38391	Scuff & Clean	Gallon
38398	Scuff & Clean	16 oz. Tube
50842	4.2 VOC Euro Extra Fast Activator	2.5 Liter
50852	4.2 VOC Euro Fast Activator	2.5 Liter
50862	4.2 VOC Euro Medium Activator	2.5 Liter
50872	4.2 VOC Euro Slow Activator	2.5 Liter
50918	Accelerator	Pint
50928	Extender	Pint
77743	XXX Gun Cleaner	20 oz. Aerosol
77763	XXX Universal Gun Cleaner	20 oz. Aerosol

RELATED PRODUCTS:

77771	XXX Universal Surface Cleaner	Gallon
77774	XXX Universal Surface Cleaner	Quart

Technical Consultation Service

Our Technical Staff is ready to assist you with any questions. You are invited to take advantage of our extensive experience, laboratory services and trained field service representatives. Call (800) 831-1122 for answers to your questions. Hours of operation are Monday through Thursday 8:00 am until 5:00 pm EST and on Friday 8:00 am until 4:30 pm EST.

Disclaimer:

The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed. All users of the materials are responsible for assuring that it is suitable for their needs, environment and use. All data subject to change as SEM deems appropriate.

Users should review the Safety Data Sheet (SDS) and product label for the material to determine possible health hazards, appropriate engineering controls and precautions to be observed in using the material. Copies of the SDS and product label are available upon request.